



EPO PR WT 851

Epoxy based, two components, low viscosity, moisture tolerant and high strength primer

DESCRIPTION:

Epoxy based, two components, low viscosity, moisture tolerant and high strength primer product.

ADVANTAGES:

It is used as a coating primer for humidity concrete surfaces.
Solvent free
Easy application
Excellent adhesion with absorbent surfaces.
Dry in a short time.
It perfectly covers the surface as homogeneously.
Fast application
Creates a glossy film.
Resistant to general cleaning chemicals.
Can be used as a primer with all type of the epoxy product.

USAGE AREAS:

In and out applications,
Mall and shopping centers,
Protection cover in industrial surface systems,
Sewage and waste facilities,
Car park and pedestrian streets,
Paper pulp and paper facilities,

Used as a primer for PU and epoxy systems,

TECHNICAL SPESIFICATION :

(23 °C Temperature and 50 % for relative humidity)

Color : Transparent - Xanthic

Density 20°C: 1,1 gr/cm³

Mixing Ratio : 2 / 1 weight

Flash Point : >60 °C

Application Temperature : +5°C +30°C

Heat Resistance : 121 °C Dry

Compressive Strenght : ~ 85 N / mm²

Bending Strenght : ~ 25 N / mm²

Adherance (Concrate) : >1,5 N / mm²

Shelf Life : 12 months

Consume : 0,200 – 0,500 Kg /m²

Solid Content : %100

Pot Life : 30 minutes (20°C de)

Dry Time : 6 hours

Coating Again : 8-24 hours

Total Dry : 7 days

***These values were obtained as a result of laboratory tests, just contain finished applications according to drying time performance. Due to differences in temperature and humidity values in the



EPO PR WT 851

Epoxy based, two components, low viscosity, moisture tolerant and high strength primer

construction site, the values may change.

APPLICATION METHOD:

Surface Preparation:

The surface; must be cured, dry and durable. Loose surface mortar and such as residues should be cleaned and reached durable surface.

In case of the necessity the surface should be cleaned mechanically

Oil, grease, dirt, paint, salt and vomiting that prevent adhesion should be removed.

If there are segregation, pits and fractures on the surface, it should be repaired with repair mortar prepared by mixing with sand with **DAYMAN EPO MORTAR, EPO - GROUT** or **EPO - SAND**.

Floor humidity must be max. 5 %.

On the moisture surfaces should be used **DAYMAN EPO - PR WT**.

Preparation Of The Mixture:

Must be ensure that the temperature of the product is between +15°C to +25°C before the mixing.

Before starting A and B components, the packages should be 400 rpm until they reach homogeneous consistency.

It should be mixed with a speed mixer.

Mixed A + B should be mixed by a 400 rpm low speed mixer for a few minutes until it reaches a homogenous consistency to make ready the primer for the application.

Remain parts of the mixing bowl and spread part of the product should be added in to mixing

The mixed product should be transferred to cleaned bowl when it ready and should re-mixed.

Pot life of the mixed product is 25°C'de 45 second.

High temperatures will make shorter the pot life of the mixed product, low temperatures will make longer.

Application:

Ready product should be applied by roll, brush and trowel.

Mixed product should be used before the pot life.

The expired, gelling mixture should not be used and should be disposed of.

ISSUES TO BE CONSIDERED:

The product is ready in sets and should not be divided and the eye decision and mixed.

Temperature should be between +5 °C and +35 °C during the application.



EPO PR WT 851

Epoxy based, two components, low viscosity, moisture tolerant and high strength primer

Do not apply on surfaces that are at risk of frost.

In addition, it should not be applied in extremely hot, rainy or windy weather.

Ensure that the ambient and floor temperature is between 5 ° C and 30 ° C.

Products should be stored at room temperature 24 hours before use.

In cold weather, the reaction will slow down due to the increase in viscosity and the application time will be longer,

the consumption will increase. Therefore, it is the most suitable temperature range between 20 ° C and 25 ° C for easy application of environment and products.

At high temperatures, the reaction and application time interval will be accelerated.

After the application, it should be protected from rain, water, frost and negative external factors for 24 hours.

CLEANING OF INSTRUMENTS:

DAYMAN PRO - WT 851 should be cleaned by solvent when it wet.

DAYMAN PRO-WT 851 after become dry should be cleaned by the mechanical ways.

CONSUME:

0,200 - 0,500 kg / m² depending on surface absorbency.

PACKING:

A +B component: 18, 00 kg

Pallet 120x80

Qty on pallet 16 set-36 bin

COLOR:

Transparent

SHELF LIFE:

1 year from the production date under proper storage conditions.

Opened packages should be kept tightly closed.

Wear suitable protective clothing, protective gloves, goggles and mask during application.

SAFETY RECOMMENDATIONS:

1 year from the production date under proper storage conditions.

Should be storage between the temperature of the DAYMAN EPO - PR 850 5 °C with 25° C



EPO PR WT 851

Epoxy based, two components, low viscosity, moisture tolerant and high strength primer

LIMITATIONS OF LIABILITY:

The information in this technical data sheet is given according to technical information, experience and test result.

As GENERALTÜRK A.Ş. cannot control the usage of the product that used under which kind of conditions, it does not accept any responsibility for the application result and does not guarantee it.


The product suitability for the product user should be tested and decided accordingly.

All products should be considered in the advice of those technical knowledge and equipment.

GENERAL TURK A.Ş can not accept any responsibility that occurs because of miss-use, it only responsible for the written suggestions that shows the products where and how use.

GENERALTÜRK A.Ş. It may change the properties of its products without announcement.

The technical data sheet is valid until the next time it is printed and all previous technical data sheets invalidate the description / January 2020

 2765	
GENERALTURK TEKNİK YALITIM KİMYA END. SAN. TİC. A.Ş. YUNUSELİ MH. 15. YAVUZ SK. NO: 21 OSMANGAZI - BURSA / TÜRKİYE 20	
2765 - CPR - 0157 EN 1504 - 2	
EPO PR WT 851	
PRODUCTS AND SYSTEMS FOR THE PROTECTION AND	
Principle 1 (PI): Protection against Ingress, Method 13. Coating ©	
Principle 2 (MC): Moisture Control, Method 2.2 Coating ©	
Color	Transparent - Xanthic
Application Temperature	: +5°C +30°C